

ABSTRACT

A winding film made of polypropylene copolymers, having a thickness of 30 -180 Nm. The strength thereof in the direction of travel at 1 % expansion corresponds to a value of 0.6 - 4 N/cm and the strength thereof at 100 % expansion corresponds to a value of 2 - 20 N/cm; the crystallite melting point of the polypropylene copolymer is less than 166 DEG C and the amount of flame proofing agent is at least 40 phr.